U 80 & U 90 KERATHERM® silicone free Thermal Tape

Benefits


- · Silicone free (polyurethane)
- · Very high thermal performance
- Good ratio between thermal performance and electrical isolation
- Softening effect for an additional increase in heat output
- \cdot Non sticky, available with adhesive coating


_	0.6
ois 90	
e es C ss	0.4 0.4
Compression U 80 & U 90	0.5 0.4 0.3
	0.2
	0.1
	10 20 30 40 50 60 70
	pressure [N/cm²]
	Rth [K/W] — Rti [Kin²/W] —
U 90	

Properties	Unit	U 80	U 90
Colour		blue	light blue
Thermal Properties*			
Thermal resistance $R_{\rm th}$	K/W	0.2*	0.082**
Thermal impedance R_{ti}	°Cmm²/W	73*	33**
	Kin²/W	0.11*	0.05**
Thermal conductivity $\boldsymbol{\lambda}$	W/mK	1.8*	6.0**
Electrical Properties**			
Dielectric breakdown voltage U _{d;AC}	kV	4.0*	4.0**
Volume resistivity	Ωm	$1.4 \times 10^{14^{*}}$	2.0 x 10 ^{-11**}
Dielectric loss factor tan $\boldsymbol{\delta}$		$1.3 \times 10^{-2*}$	1.4 x 10 ^{-2**}
Dielectric constant $\epsilon_{\rm r}$		3.2*	3.1**
Mechanical Properties			
Hardness	Shore A	80 - 90	70 - 85
Tensile strength	N/mm²	3.0	2.0
Elongation	%	130	150
Physical Properties			
Application temperature	°C	-40 to +125	-40 to +125
Density	g/cm³	2.26	1.46
Flame rating	UL-94	V-O	V-0
Possible thickness	mm	0.15 - 0.3	0.1-0.3











Note

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. KERAFOL® is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. All specifications are subject to change without notice. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded. In case KERAFOL® would be nevertheless held liable, on whatever legal ground, KERAFOL®'s liability will in no event exceed the amount of the concerned delivery. All KERAFOL® products are sold pursuant to the KERAFOL®'s Terms and Conditions of sale and delivery in effect from time to time, a copy of which will be furnished upon request.

05-2024